

# TEMPEST

700.682

## Description

Water based paint stripper for antifouling and one component products, easy to apply, it can be used on various surfaces: wood, metal, fiberglass and plastic. Free from noxious chemical compounds and it does not produce toxic vapours and will not damage the gelcoat or epoxy primers.

## Use

Paint stripper indicated for one component paints removal such as old anti-fouling.

## Informations

Finish	Thixotropic coloured paste	
Colours	.001 Light blue	
Pack	2,5 l	
Specific Gravity	1,10 – 1,15 g/cm <sup>3</sup>	ISO 2811-1
Flash Point	20 °C	ISO 3679
VOC	305 g/l	Calculated
Shelf Life	36 months	

## Application

Use only in surfaces not exposed to sunlight.

Apply a thickness of at least 2 - 3 mm.

Allow it to react between 2 to 3 hours, depending on the weather conditions.


Remove the soft mixture with a scraper or with high pressure fresh water. If necessary, repeat the operation.

After drying, abrade the treated area with sandpaper grade P180 - P220.

Rinse with fresh water and let it dry for at least 24 hours.

Before painting, the surface must be perfectly clean, dry and free of oil and contaminants.

## How to Apply

Standard		Brush and roller
----------	---	------------------

## Additional Application Information

Theoretical spreading rate	Application range at the recommended thickness: 2 - 3 m <sup>2</sup> /l
----------------------------	--

## Conditions during application

During application and curing:

Ambient temperature: minimum 10°C, maximum 35 °C.

Minimum substrate temperature 10 °C (if during the curing the temperature drops below 10 °C, overcoating will take additional time).

Avoid the formation of condensation, the surface temperature should be at least 3 °C above dew point.

Maximum relative humidity 85%.

Painting area should be well ventilated, during application and drying/curing.

## Storage

It is recommended to avoid exposure to air and extreme temperatures. To maximize the shelf life in the can, check that the container is closed during the storage and the temperature is between 5 °C and 35 °C.

Avoid exposure to direct sunlight.



# TEMPEST

700.682

## Safety Rules

Comply with the provisions set by the local health and safety at work regulations. Avoid contact with the skin, operate in well-ventilated places and, if in closed areas, use vacuum cleaners, fans and air conveyors. During the application use appropriate PPE - Personal Protections Equipment (masks, gloves, glasses, etc.). Before using, read sections 7-8 of the SDS.

### INSTRUCTIONS FOR THE DISPOSAL OF THE BIOCIDAL PRODUCTS AND PACKAGING

Empty packaging containing biocidal products: disposal of empty packaging according to the requirements of the waste disposal law, for example by taking them to the recycling centre. Packages containing the unused biocidal product: Dispose of the product not used in accordance with the law of disposal of such waste, for example by taking it to a recycling centre, recycling of packaging is prohibited in this case. Do not empty into drains or watercourses.

### INSTRUCTIONS FOR THE SAFETY SECURITY OF THE BIOCIDAL PRODUCTS AND PACKAGING

Empty containers and containers still containing the biocidal product: Packaging must be disposed of as hazardous waste under the full responsibility of the holder of such waste. Do not empty into drains or watercourses.

## Disclaimer

The values indicated in the present technical sheet can have slight variations from one batch to another. The applied product must not come in contact with water, chemicals or subjected to mechanical stress before the curing is complete. The wet film thickness refers to the undiluted product. In case of dilution, this value increases. The above information is the result of accurate laboratory tests and practical experience, however, since the product is predominantly used outside the manufacturer's control, Boero Bartolomeo S.p.A. can only guarantee their quality. The information contained in this sheet may be subject to revision by the Company. For clarification, updates or further information, it is recommended to contact Boero Bartolomeo S.p.A. directly. The present datasheet annuls and replaces every other precedent to this one.